



SPRAY P 360 2K HS PRIMER

Technical Data Sheet No 807



VOC compliant with the regulations

Excellent spray primer, suitable for metal surfaces

It is paintable with all 2K systems of primers and top coats

It dries after 10 min

General Technical Description

2-3 passes

Dust free 10 mins at 23°C

Surface

On old, sanded paint work

OEM surfaces

Thermoplastic Coatings - TPA

Fiberglass

Clean and sanded steel panels

HB Body Polyester Fillers

HB Body 960 Wash Primer

Bodyfill 961 Etch Filling Primer

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST.

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

Product Application: »» Apply two to three medium coats necessary to cover the area waiting 10-12 mins in between each coat. Each coat should appear uniform and dry. Light wet sanding before basecoat application using a P800-P1000 grit paper



Shake well before using

Flash Point:
-97°C



2-3 coats approximately 20-30 microns

Specific Gravity:
0.94 g/cm³

Solid Content (No thinner):
50%



Dust free 10min at 23 °C

VOC (2004/42/EC)
This product is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 490g/L.
2004/42/II(b)(840)490



Spray at a distance of 25 cm thinly applied coats build up within 10-12 min intervals will achieve best results.

Theoretical Coverage:
-

Cleaning of equipment:
-

Remarks:

- Always try to use the product in accordance with the specifications provided.
- It can be used by countries that do not adopt the VOC legislation as well.
- Shake thoroughly before use.
- Shake for 1-2 mins after agitator ball has started to rattle.
- After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.
- Optimum operating temperature range 10-25°C.

Storage shelf life:

Store in a cool place and use within 36 months for best results.
+5 to +25 °C

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 5 / 2016, December 2016